

Fiche technique **MA-200X100-10G**

Proprietes	Normes	Unite	Ø	Min	Max	Autre
polymère						
Specifications	Öko-Tex					Standard 100
Densite	DIN EN ISO 845	kg/m ³		20	24	
Resistance traction	DIN EN ISO 1798	kPa		100		
Allongement a la rupture	DIN EN ISO 1798	%		120		
Resistance compression	DIN EN ISO 3386-1 40%deformation	kPa		3	5	
Jeu de compression	DIN EN ISO 1856	%			10	
Classification non feu						non